

Provisional Technical Datasheet

F0146D Polysure HDPE

HD Film

Product Characteristics:

Polysure F0146D is a 1-Hexene co-monomer based High Density Polyethylene, produced by Advanced Dual Loop Slurry MarTECH™ technology, suitable for Blown Film Extrusion process. F0146D resin comes with a combination of excellent processability, good bubble stability, superb mechanical properties and high filler loading characteristics.

Recommended Applications:

General purpose packaging, Kirana bags, Shopping bags, T-shirt bags, Liners, Trash bags, Multilayer films

Typical Properties:

Sr. No.	Property	Test Method	Unit	Value*
Resin Properties				
1	Melt Flow Index (190°C & 2.16 kg)	ASTM D1238	g/10 min	0.18
2	Density (23°C)	ASTM D1505	g/cc	0.946
Film Properties*				
1	Tensile Strength at Yield (MD/TD)	ASTM D882 (50 mm / min)	MPa	24 / 26
2	Tensile Strength at Break (MD/TD)		MPa	50 / 30
3	Tensile Elongation at Break (MD/TD)		%	480 / 640
4	Elmendorf Tear Strength (MD/TD)	ASTM D1922	g/micron	0.8 / 10.8
5	Dart Impact Strength	ASTM D1709A	g/micron	3.6

*The film properties have been measured on 25 µm thick films (Blow-up ratio: 4, Die Gap : 1 mm)

Processing Guidelines:

- Barrel Temperature : 180 - 220°C
- Die Temperature : 190 - 210°C

Storage & Handling:

Bags should be stored in dry & dust free environment at temperature below 50°C and Prevent from direct exposure to sunlight & heat to avoid quality deterioration.

Regulatory Requirements:

F0146D to be manufactured complying the requirements specified in IS 10146 on "Specification for Polyethylene for its safe in contact with Foodstuff, Pharmaceutical & Drinking water". Furthermore, the Additives added in this grade formulation compiles to the "Positive list of constituents for Polypropylene, Polyethylene and their Copolymers for its safe use in contact with Foodstuffs & Pharmaceuticals" as laid down under IS 16738:2018. In general, the additives & constituents used in the grade are in line with requirement laid down under FDA: CFR Title 21,177.1520, Olefin Polymers.

Updated as of May 2021

Disclaimer: The information & data presented herein are typical values & should not be considered as specification and may be used as guideline only. HMEL does not undertake any responsibility for any outcome or results from the adoption or replication of the above-mentioned data & information there on for possible use for various applications. HMEL reserves the right to change the information & data without any prior notice or information. The user will solely be responsible for any process/product usage.

HPCL-Mittal Energy Limited (HMEL), INOX Tower, Plot No.17, Sector-16A, Noida – 201301 (U.P), India. Tel: 0120-4634500. Corporate Site: www.hmel.in